Technical Product Information

WPS II

Heat sink paste



austerlitz electronic



Examples of Application

 To optimize heat transfer between electronic construction elements and cooling bodies of low to medium power density, such as semi-conductors (transistors, diodes, thyristors, etc.) as well as other integrated components

Properties

- Free from silicone
- Very good low temperature properties

Characteristic data

- Service temperature: -40 °C to +150 °C
- Appearance: white-grey
- NLGI grade: 2 3*

| Thickener | Bentonite/metal oxides | | |
|-------------------------------|------------------------|-------------|--------------|
| Unworked penetration | 1/10 mm | 250 - 290 | DIN ISO 2137 |
| Thermal conductivity at 25 °C | W/mK | approx. 0,5 | Method PTB** |
| Oil separation (40 °C/168 h) | % | ≤ 2 | DIN 51817 |
| Flow pressure at +20 °C | mbar | ≤ 200 | DIN 51805 |
| Base oil | Synthetic ester | | |
| Kin. viscosity at 40 °C | mm²/s | approx. 90 | DIN 51562 |
| Kin. viscosity at 100 °C | mm²/s | approx. 13 | DIN 51562 |

Instructions for use

- Product has to be processed or consumed within 6 months from production date
- Tubes filled within this period have a shelf life of 3 years from filling date
- · Prior to serial production product compatibility tests are recommended
- · For construction parts without high frequency exposure only
- * The indication refers to the unworked penetration
- ** Physical-Technical Federal Office Braunschweig and Berlin (transient hot bridge)

austerlitz electronic gmbh

Ludwig-Feuerbach-Str. 38 90489 Nürnberg · Germany Phone +49 911 59 747-0 Fax +49 911 59 747-89 info@austerlitz-electronic.de www.austerlitz-electronic.de

The above data correspond to latest technology, modifications reserved. This information is intended as a guide and does not necessarily represent a marketing specification. In individual cases tests have to be carried out by the consumer. Further data upon request.